



MATERIAL PROPERTY TEST REPORT

Test Standard: General Motors GMW16214, Type 3 (2015)
Material Type: Expanded Polypropylene Foam HB Series
Testing Completed & Certified by: MGA Labs. Greer, SC, USA (A2LA Cert. 850.02)
Product Type: HB Series

PROPERTY/TEST	PRINT** SPECIFICATION	SPECIMEN RESULTS	TEST METHOD
Density, g/l or kg/m ³ (40 g/l ±10%),	36-44	39	ISO 845
Tensile Strength KPa, Min	300	530	ISO 1926
Tensile Elongation %, Min	10	11	ISO 1926
Compression, Stress 50% Strain, KPa, Min	180	286	ISO 844
Compression Set 22 h at 50% Comp, KPa, Max	45	33	ISO 1856
Flammability As Received	100	56	FMVSS-302 (per GMW3232)
Heat Aged, Max (mm/min)	100	64	
Resistance to Odor Rating	Rating >6	Rating = 8	GMW3205-B2
Emission Analysis VOC Value; micro-g/g, Target ≤	100	12	GMW15634
Fog Value; micro-g/, Target ≤	250	28	
Fogging Mg/Max	2	0.4	GMW3235-B-Y1-T1

This certifies that the above material meets the requirements for the Production Part Approval Process per the General Motors Engineering Specification GMW16214 for Type 3 for 2015

William A. Pate

Date 4/23/2015

William Pate, Technical Service Manager
Hanwha Advanced Materials America LLC